

Enchant



| | | | | | <u>S</u> | × |
|--------------------------|--------|-----------|-------------|-------|----------|-------|
| NOMINAL SIZE | FINISH | THICKNESS | GROUT JOINT | MYSTI | OAS | SPARK |
| 8 x 40 Rectified | Matte | 9 mm | 1/8" | ✓ | V | ✓ |
| 8 x 40 Chevron Rectified | Matte | 9 mm | 1/8" | ŭ | v | ŭ |
| 2.5 x 19 Listel Mosaic | Matte | 9 mm | N/A | v | v | U |
| 2.5 x 20 Bullnose | Matte | 9 mm | 1/8″ | U | U | O |

✓ Stock Item. U Non-Stock Item. Requires Extra Lead Time.

TECH INFO

R = Residential, LC = Light Commercial, C = Commercia

| ORIGIN: USA | RECOMMENDED APPLICATIONS | | LC | С |
|---|-----------------------------|---|----|---|
| SHADE VARIATION: V3 - Moderate Variation | FLOORS | • | • | • |
| WEAR RATING: Class 5 - Rated for all residential and commercial applications | WALLS / BACKSPLASH | • | • | |
| It is not recommended to stagger any tile longer than 15" more than 1/3 the length of the tile. | PO <mark>OL D</mark> ECKING | * | * | * |
| | EXTERNAL USE - FROST PROOF | * | * | * |

Approved for this applicatio

TILE PERFORMANCE DATA

| TECHNICAL FEATURE | NORMS | RESULTS ≤ 0.5 % | |
|-------------------------------------|------------|-----------------|--|
| Water Absorption | ASTM C373 | | |
| Breaking Strength | ASTM C648 | ≥ 250 lbs | |
| Dynamic Coefficient of Friction Wet | AcuTest | 0.42 | |
| Thickness Dimension | ASTM C499 | In accordance | |
| Facial Dimension | ASTM C499 | In accordance | |
| Warpage Diagonal | ASTM C485 | In accordance | |
| Wedging | ASTM C502 | In accordance | |
| Frost Resistance | ASTM C1026 | Frost Proof | |
| Scratch Hardness | MOHS | 6 | |

^{*} Discuss proper installation method with your Sales Representative