

Fabric Look

PORCELAIN

BEST TILE® / BESTTILE.COM

Coventry



COLORS, SIZES & AVAILABILITY

NOMINAL SIZE	FINISH	THICKNESS	GROUT JOINT	CARBON	CONCRETE	COTTON	MUD	OCEAN	PINE GREEN	SAND	SUNFLOWER
3 x 16	Glossy	8.5 mm	3/16"	✓	✓	✓	✓	✓	✓		✓
12 x 24 Rectified	Matte	8.5 mm	1/8"		✓	✓	✓	✓		✓	
24 x 24 Rectified	Matte	8.5 mm	1/8"		⊖	⊖	⊖	⊖		⊖	
24 x 48 Rectified	Matte	8.5 mm	1/8"		⊖	⊖	⊖	⊖		⊖	
32 x 32 Rectified	Matte	8.5 mm	1/8"		⊖	⊖	⊖	⊖		⊖	
48 x 48 Rectified	Matte	8.5 mm	1/8"		⊖	⊖	⊖	⊖		⊖	
Modernist Mosaic	Matte	8.5 mm	1/8"		✓	✓	✓	✓		✓	
2 x 2 Mosaic	Matte	8.5 mm	N/A		✓	✓	✓	✓		✓	
2 x 3 Hexagon Mosaic	Matte	8.5 mm	N/A		✓	✓	✓	✓		✓	
3 x 24 Bullnose	Matte	8.5 mm	1/8"		✓	✓	✓	✓		✓	

✓ Stock Item. ⊖ Non-Stock Item. Requires Extra Lead Time.

TECH INFO

R = Residential, LC = Light Commercial, C = Commercial

ORIGIN: Italy SHADE VARIATION: V2 - Slight Variation WEAR RATING: 3x16 Glossy: 1 - Wall Applications Only; All Matte sizes: 5 - Walls + Residential / Commercial Floor Applications It is not recommended to stagger any tile longer than 15" more than 1/3 the length of the tile.	RECOMMENDED APPLICATIONS	R	LC	C
	FLOORS	+	+	+
	WALLS / BACKSPLASH	●	●	●
	POOL DECKING			
	EXTERNAL USE - FROST PROOF	*	*	*

● Approved for this application. + Matte approved for this application. * Discuss proper installation method with your Sales Representative.

TILE PERFORMANCE DATA

TECHNICAL FEATURE	NORMS	RESULTS
Water Absorption	ISO 10545-3	0.10 %
Deep Abrasion	ISO 10545-6	135 mm ³
Breaking Strength	ISO 10545-4	≥ 35 N/mm ²
Dynamic Coefficient of Friction Wet	AcuTest	≥ 0.42
Dimensions Range	ISO 10545-2	Conforms
Frost Resistance	ISO 10545-12	Frost Proof
Chemical Resistance - Household Chemicals	ISO 10545-13	Min. Class GB
Thermal Shock Resistance	ISO 10545-9	Resists
Resistance to Stains	ISO 10545-14	Min. Class 3

Always inspect materials prior to installation. Always mix 2-3 cartons at a time while installing to ensure the best blend. All product images are representative only. Variation in color and shading is to be expected. Final selection should be made from actual tile samples.